

# Bond-Ply® 800

Thermally Conductive, Fiberglass Reinforced Pressure Sensitive Adhesive Tape

## Features and Benefits

- Thermal impedance:  
0.60°C-in<sup>2</sup>/W (@50 psi)
- High bond strength to most epoxies and metals
- Double-sided, pressure sensitive adhesive tape
- High performance, thermally conductive acrylic adhesive
- More cost-effective than heat-cure adhesive, screw mounting or clip mounting



Bond-Ply® 800 is a thermally conductive, electrically isolating double-sided tape.

Bond-Ply® 800 is utilized in lighting applications that require thermal transfer and electric isolation. High bond strengths obtained at ambient temperature lead to significant processing cost savings in labor, materials and throughput due to the elimination of mechanical fasteners and high temperature curing.

## Typical Applications Include:

- Mount LED assembly to troffer housing
- Mount LED assembly to heat sink
- Mount heat spreader onto power converter PCB or onto motor control PCB
- Mount heat sink to BGA graphic processor or drive processor

## Configurations Available:


- Sheet form, roll form and die-cut parts

### TYPICAL PROPERTIES OF BOND-PLY 800

PROPERTY	IMPERIAL VALUE	METRIC VALUE	TEST METHOD		
Color	Gray	Gray	Visual		
Reinforcement Carrier	Fiberglass	Fiberglass	—		
Thickness (inch) / (mm)	0.005, 0.008	0.127, 0.203	ASTM D374		
Elongation (% , 45° to Warp & Fill)	70	70	ASTM D412		
Tensile Strength (psi) / (MPa)	1500	10	ASTM D412		
CTE (um/m·°C), -40°C to +125°C	600	600	ASTM D3386		
Continuous Use Temp (°F) / (°C)	-40 to 257	-40 to 125	—		
<b>ADHESION</b>					
Lap Shear @ RT (psi) / (MPa) (1)	150	1.0	ASTM D1002		
<b>ELECTRICAL</b>		<b>VALUE</b>	<b>TEST METHOD</b>		
Dielectric Breakdown Voltage (Vac), 0.005		4000	ASTM D149		
Dielectric Breakdown Voltage (Vac), 0.008		6000	ASTM D149		
Dielectric Constant (1000 Hz)		4.0	ASTM D150		
Volume Resistivity (Ohm-meter)		10 <sup>11</sup>	ASTM D257		
Flame Rating		V-O	U.L. 94		
<b>THERMAL</b>					
Thermal Conductivity (W/m-K)		0.8	ASTM D5470		
<b>THERMAL PERFORMANCE vs PRESSURE</b>					
<b>Initial Assembly Pressure (psi for 5 seconds)</b>	<b>10</b>	<b>25</b>	<b>50</b>	<b>100</b>	<b>200</b>
TO-220 Thermal Performance (°C/W), 0.005	5.0	5.0	4.8	4.3	4.2
TO-220 Thermal Performance (°C/W), 0.008	6.2	6.0	5.6	5.3	5.2
Thermal Impedance (°C-in <sup>2</sup> /W), 0.005 (2)	0.63	0.62	0.60	0.58	0.57
Thermal Impedance (°C-in <sup>2</sup> /W), 0.008 (2)	0.78	0.74	0.72	0.71	0.71

1) Tested per ASTM D1002 with aluminum lap shear samples, 75 psi applied for 5 seconds then pressure removed. 0.5 square inch Bond-Ply 800 sample.  
2) The ASTM D5470 test fixture was used. The recorded value includes interfacial thermal resistance. These values are provided for reference only. Actual application performance is directly related to the surface roughness, flatness and pressure applied.

## Building a Part Number



## Standard Options

◀ example

NA = Selected standard option. If not selecting a standard option, insert company name, drawing number, and revision level.

1212 = 12" x 12" sheets, 12250 = 12" x 250' rolls or 00 = custom configuration

00 = Standard double-sided adhesive

Standard thicknesses available: 0.005", 0.008"

BP800 = Bond-Ply 800 Material

Note: To build a part number, visit our website at [www.bergquistcompany.com](http://www.bergquistcompany.com).



[www.bergquistcompany.com](http://www.bergquistcompany.com)

The Bergquist Company -  
North American Headquarters  
18930 West 78th Street  
Chanhassen, MN 55317  
Phone: 800-347-4572  
Fax: 952-835-0430

The Bergquist Company -  
European Headquarters  
Netherlands  
Phone: 31-35-5380684  
Fax: 31-35-5380295

The Bergquist Company -  
Asia Headquarters  
Hong Kong  
Phone: 852-2690-9296  
Fax: 852-2690-3408

All statements, technical information and recommendations herein are based on tests we believe to be reliable, and THE FOLLOWING IS MADE IN LIEU OF ALL WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MARKETABILITY AND FITNESS FOR PURPOSE. Sellers' and manufacturers' only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use, and the user assumes all risks and liability whatsoever in connection therewith. NEITHER SELLER NOR MANUFACTURER SHALL BE LIABLE EITHER IN TORT OR IN CONTRACT FOR ANY LOSS OR DAMAGE, DIRECT, INCIDENTAL, OR CONSEQUENTIAL, INCLUDING LOSS OF PROFITS OR REVENUE ARISING OUT OF THE USE OR THE INABILITY TO USE A PRODUCT. No statement, purchase order or recommendations by seller or purchaser not contained herein shall have any force or effect unless in an agreement signed by the officers of the seller and manufacturer.

PDS\_BP800\_0714