

Features and Benefits

- Thermal impedance: 0.82°C-in²/W (@50 psi)
- Polyester based
- For applications requiring non-silicone conformal coatings
- Designed for silicone-sensitive applications requiring high performance



Poly-Pad 1000 is a fiberglass-reinforced insulator coated with a filled polyester resin. The material offers superior thermal resistance for high performance applications.

Polyester-based, thermally conductive insulators from Bergquist provide a complete family of materials for silicone-sensitive applications. Poly-Pads are ideally suited for applications requiring conformal coatings or applications where silicone contamination is a concern (telecomm and certain aerospace applications). Poly-Pads are constructed with ceramic-filled polyester resins coating either side of a fiberglass carrier or a film carrier. The Poly-Pad family offers a complete range of performance characteristics to match individual applications.

| TYPICAL PROPERTIES OF POLY-PAD 1000 | | | | | | |
|--|------------------|------------------|-------------|------|------|------|
| PROPERTY | IMPERIAL VALUE | METRIC VALUE | TEST METHOD | | | |
| Color | Yellow | Yellow | Visual | | | |
| Reinforcement Carrier | Fiberglass | Fiberglass | — | | | |
| Thickness (inch) / (mm) | 0.009 | 0.229 | ASTM D374 | | | |
| Hardness (Shore A) | 90 | 90 | ASTM D2240 | | | |
| Breaking Strength (lbs/inch) / (kN/m) | 100 | 18 | ASTM D1458 | | | |
| Elongation (%) | 10 | 10 | ASTM D412 | | | |
| Tensile Strength (psi) / (MPa) | 7000 | 48 | ASTM D412 | | | |
| Continuous Use Temp (°F) / (°C) | -4 to 302 | -20 to 150 | — | | | |
| ELECTRICAL | | | | | | |
| Dielectric Breakdown Voltage (Vac) | 2500 | 2500 | ASTM D149 | | | |
| Dielectric Constant (1000 Hz) | 4.5 | 4.5 | ASTM D150 | | | |
| Volume Resistivity (Ohm-meter) | 10 ¹¹ | 10 ¹¹ | ASTM D257 | | | |
| THERMAL | | | | | | |
| Thermal Conductivity (W/m-K) | 1.2 | 1.2 | ASTM D5470 | | | |
| THERMAL PERFORMANCE vs PRESSURE | | | | | | |
| | Pressure (psi) | 10 | 25 | 50 | 100 | 200 |
| TO-220 Thermal Performance (°C/W) | | 4.70 | 4.25 | 3.74 | 3.27 | 2.89 |
| Thermal Impedance (°C-in ² /W) (1) | | 1.30 | 1.02 | 0.82 | 0.61 | 0.43 |
| 1) The ASTM D5470 test fixture was used. The recorded value includes interfacial thermal resistance. These values are provided for reference only. Actual application performance is directly related to the surface roughness, flatness and pressure applied. | | | | | | |


Typical Applications Include:

- Power supplies
- Automotive electronics
- Motor controls
- Power semiconductors

Configurations Available:

- Sheet form, die-cut parts and roll form
- With or without pressure sensitive adhesive

Building a Part Number



Standard Options

◀ example

NA = Selected standard option. If not selecting a standard option, insert company name, drawing number, and revision level.

___ = Standard configuration dash number, 1212 = 12" x 12" sheets, 12/250 = 12" x 250' rolls, or 00 = custom configuration

AC = Adhesive, one side
00 = No adhesive

Standard thicknesses available: 0.009"

PP1000 = Poly-Pad 1000 Material

Note: To build a part number, visit our website at www.bergquistcompany.com.

Sil-Pad®: U.S. Patents 4,574,879; 4,602,125; 4,602,678; 4,685,987; 4,842,911 and others



www.bergquistcompany.com

The Bergquist Company -
North American Headquarters
18930 West 78th Street
Chanhassen, MN 55317
Phone: 800-347-4572
Fax: 952-835-0430

The Bergquist Company -
European Headquarters
Bramenberg 9a, 3755 BT Eemnes
Netherlands
Phone: 31-35-5380684
Fax: 31-35-5380295

The Bergquist Company - Asia
Room 15, 8/F Wah Wai Industrial Centre
No. 38-40, Au Pui Wan Street
Fotan, Shatin, N.T. Hong Kong
Ph: 852.2690.9296
Fax: 852.2690.2344

All statements, technical information and recommendations herein are based on tests we believe to be reliable, and THE FOLLOWING IS MADE IN LIEU OF ALL WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MARKETABILITY AND FITNESS FOR PURPOSE. Sellers and manufacturers' only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use, and the user assumes all risks and liability whatsoever in connection therewith. NEITHER SELLER NOR MANUFACTURER SHALL BE LIABLE EITHER IN TORT OR IN CONTRACT FOR ANY LOSS OR DAMAGE, DIRECT, INCIDENTAL OR CONSEQUENTIAL, INCLUDING LOSS OF PROFITS OR REVENUE ARISING OUT OF THE USE OR THE INABILITY TO USE A PRODUCT. No statement, purchase order or recommendations by seller or purchaser not contained herein shall have any force or effect unless in an agreement signed by the officers of the seller and manufacturer.