

H.B. Fuller Company P.O. Box 64683 St. Paul, MN 55164-0683

Page 1 of 2

TECHNICAL DATA SHEET

HOT MELT ADHESIVE

DESCRIPTION

This is a general purpose pressure sensitive adhesive with excellent adhesion to a wide variety of substrates.

FDA STATUS: A letter is available upon request.

TYPICAL PHYSICAL PROPERTIES and GENERAL INFORMATION

RAW MATERIAL BASE	SYNTHETIC RESIN
90 DEGREE PEEL TEST	3.2 LBS/LIN IN
180 DEGREE PEEL (60 SEC/75F, 1 MIL)	7.3 LBS/INCH
MOLTEN GARDNER COLOR	7
POLYKEN TACK	1,100 GRAMS
LOOP TACK	130 OUNCES
VISCOSITY @ 300F	40,000 cP (mPa.s)
VISCOSITY @ 350F	9,000 cP (mPa.s)
WEIGHT PER GALLON	7.72 POUNDS
SAFT (500 GMS/IN2 LOAD)	175 DEGREES F.
SHELF LIFE	ONE YEAR
FORM & PACKAGING	PILLOW, DRUM
RECOMMENDED APPLICATION TEMPERATURE	325 F

APPLICATION AND CLEANUP

An inert gas blanket is recommended while the adhesive is molten to ensure the best retention of physical properties. Consult the equipment manufacturer for cleanup procedures, or flush the unit with mineral oil at 250F. Flush the applicator thoroughly with hot melt to purge the system.

SAFETY

To minimize the risk of burns, we recommend the use of eye protection and protective clothing when working near a hot melt applicator. To minimize the risk of flammable vapors, do not exceed a melt temperature above 400F. Prevent the build-up of vapors. Extinguish all sources of ignition during hot melt use.

Last Update: 04/17/03



H.B. Fuller Company
P.O. Box 64683

St. Paul, MN 55164-0683

HM-1597
PRODUCT NUMBER

Page 2 of 2

LIMITED WARRANTY AND TERMS

H.B. Fuller Company ("Fuller") warrants that, for a Warranty Period of one year (or the period specified on the applicable Technical Data Sheet, whichever is less) from the date of shipment from Fuller to the Initial Purchaser, that this Fuller product was manufactured in accordance with Fuller's specifications in effect on the date of manufacture. These specifications are available upon request. This Warranty does not cover test data, or any defects, damages or other harms caused to any extent or in any way by failure to follow applicable Fuller instructions, if any, or abuse or misuse of the product.

WARRANTIES_DISCLAIMED -- THE WARRANTY STATED IN THE PARAGRAPH ABOVE IS IN PLACE OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED. Fuller EXPRESSLY DISCLAIMS ANY OTHER WARRANTIES, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. ALTHOUGH Fuller MAY HAVE SUGGESTED THE PRODUCT OR DEVELOPED THE PRODUCT AT THE PURCHASER'S REQUEST, IT IS THE PURCHASER'S RESPONSIBILITY TO TEST AND DETERMINE THE SUITABILITY OF THE PRODUCT FOR THE PURCHASER'S INTENDED USE AND PURPOSE, AND PURCHASER ASSUMES ALL RISK AND LIABILITY WHATSOEVER REGARDING SUCH SUITABILITY.

LIMITATIONS_OF_REMEDIES_AND_DAMAGES -- FOR ANY VALID CLAIM PRESENTED UNDER THE LIMITED WARRANTY, Fuller WILL REPLACE THE PRODUCT, OR AT ITS OPTION, REFUND THE PURCHASE PRICE. THIS REPLACEMENT/REFUND REMEDY IS THE PURCHASER'S SOLE AND EXCLUSIVE REMEDY AGAINST Fuller. THE PURCHASER AGREES THAT NO OTHER REMEDY (INCLUDING BUT NOT LIMITED TO LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO PURCHASER FOR CLAIMS ARISING OUT OF ANY USE OF THE PRODUCT REGARDLESS OF THE LEGAL THEORY (CONTRACT, TORT OR OTHER). IN NO EVENT WILL Fuller BE OBLIGATED TO PAY DAMAGES TO PURCHASER IN ANY AMOUNT EXCEEDING THE PRICE THAT THE PURCHASER PAID FOR THE PRODUCT.

<u>LIMITATION_OF_ACTIONS_AND_VENUE</u> -- Any claim made or action commenced by Purchaser under Fuller's limited warranty as set forth herein must be brought within one year from the date of shipment from Fuller to the Purchaser. Purchaser agrees that all disputes arising from Fuller's sale of product to Purchaser shall be brought, if at all, in and before a court located in the State of Minnesota, to the exclusion of the courts of any other state.

<u>CONDITIONAL_ACCEPTANCE</u> -- Fuller's acceptance of Purchaser's order for this product is expressly conditional on Purchaser's assent to terms and conditions set forth herein.

ADEQUATE TESTS: The information contained in this bulletin we believe is correct to the best of our knowledge and tests. The recommendations and suggestions herein are made without guarantee or representation as to results. We recommend that adequate tests be made in your laboratory or plant to determine if this product meets all of your requirements.

Last Update: 04/17/03